



## Liquid accelerator for cement mortar

- flexible setting time (15 sec. – 5 min.)
- for plugging water leaks, honeycombs and cracks
- for fast setting repair mortars
- for fast setting mortars for reprofiling and repair of water leaks in channels and manholes
- chloride and solvent free
- not corrosive to reinforcing steel



### PRODUCT DESCRIPTION

VANDEX 4V is a liquid, highly alkaline additive for accelerating the setting time of cement mortar. It can be applied diluted with water or undiluted – the higher the concentration, the faster the setting. Wear rubber gloves for application.

### SETTING TIME

Undiluted VANDEX 4V*	approx. 30 sec.
Diluted VANDEX 4V* (1 part VANDEX 4V + 4 parts water)	approx. 5 min.

\* using fresh cement, temperature of material and air: 20 °C

### PACKAGING / STORAGE

In 10 l containers.

When stored in unopened, undamaged original packaging, shelf life is 24 months. Product is resistant to frost down to -20 °C.

### TECHNICAL DATA

Appearance	clear liquid
Density	approx. 1.25 kg/l
pH value	> 13
Other data	Does not contain chlorides.



## CONCRETE PROTECTION AND WATERPROOFING

### INTERNATIONAL SALES:

#### VANDEX INTERNATIONAL LTD

P.O. Box, CH-4501 Solothurn/Switzerland  
Phone: +41 32 626 36 36, Fax +41 32 626 36 37  
E-mail: info@vandex.com www.vandex.com

### PRODUCTION AND SALES GERMANY:

#### VANDEX ISOLIERMITTEL-GESELLSCHAFT m.b.H.

P.O. Box, 1406, D-21487 Schwarzenbek/Germany

